
VITO Irmen GmbH & Co. KG





Application

VITOMOUNT 125 SA-220 PLG is used for fixing trims in the automotive industry.

Product benefits

- high final adhesion strength
- very good aging, weathering and plasticiser resistance
- compatible with acrylic glass
- compensates slight roughnesses and thermal expansion

Technical data and product properties

peel adhesion on stainless steel acc. to DIN EN 1939:1996	at 20 °C	18 N/25 mm
shear adhesion on stainless steel acc. to DIN EN 1943:1996	at 20 °C at 50 °C at 70 °C at 100 °C	50 N/625 mm ² 30 N/625 mm ² 20 N/625 mm ² 10 N/625 mm ²
compatibility with acrylic glass	yes	
resistance against plasticizer	very good	
temperature resistance	-40 °C to 90 °C, short term 100 °C	
application temperature	15 °C to 30 °C	

Phone: +49(0)2642/4007-0 E-Mail: info@vito-irmen.de further information: www.vito-irmen.de





VITOMOUNT 125 SA-220 PLG

Processing

The most important processing parameters and information on cleaning are listed in our Information on Processing Adhesive Tapes.

Storage and shelf life

12 month after receipt of goods, when stored at 18 °C and 60 % relative humidity protected from sunlight, in original packaging.

Aternatives

VITOMOUNT 125 SA-220 PET, black, 0.8 mm, with PET film liner

Special Information

All data and technical information presented are based on laboratory tests or have been compiled from supplier information to the best of our knowledge. A guarantee that the values are complete and correct can however not be given. You are kindly requested to conduct your own tests to determine the suitability of our product for your applications. Our General Conditions answer any questions on guarantees and liabilities for these products insofar as no other legal regulations apply.

If you need further information about product safety, conformance, REACH or RoHS please send your e-mail to info@vito-irmen.de

06/2015 Ki

